



150 mm thick, Mineral Wool core - Density type "M"

Profile and side joint PF1

Standard profile

Micro ribbed profile

Description

ACH WALL PANEL (PF1) is manufactured with two pre painted steel sheets, bonded with organic glued to the mineral core. The steel sheets fulfill the EN10346 standards and they are available from 0.5mm to 1.00mm thick, being 0.5mm ACH's standard thickness.

To meet each project special appliance, ACH offers several coating options: SP25, PVDF25, PVDF35, HDS35, HDS35, HDS55, PRISMA55, HPS200, etc. All according to EN 10169. ACH standard coating is 25µm Polyester (SP25).

ACH WALL PANEL (PF1) can be manufactured with other materials, upon request: Aluminum, Stainless Steel, etc.
The Mineral core is produced according to EN13162 standard.

Applications

ACH WALL PANEL (PF1) is a secret fixings insulated panel specially designed for industrial and large buildings construction, as well as ceilings.

ACH WALL PANELS (PF1) are recommended for the construction of interior division walls and façades of:

- Warehousing: small, medium or large size, usually heated.
- Acoustic insulation inside industrial buildings.
- When fire protection is required or established by the Building Regulations and Standards.
- Parking and garage Firewalls, to prevent fire propagation.
- Data Centers, where fire suppression is obligatory, in addition to high temperatures and noise insulation.
- Storage buildings designed for flammable and/or combustible substances storage.
- Professional rental spaces, where activity frequently changes.

Advantages

ACH prefabricated panels advantages are: easy and fast installation, lighter structure, higher finishing quality, fire protection, acoustic and thermal insulation, time and cost saving, with the best quality certification.



Flat profile

Performance

Thickness mm	Width mm	Máx. recomended length m	Core's Type	Weight kg/m²	Thermal W/m²K
150	1.150	12,00	М	25,4	0,261

Acoustics*

R _w (dB)	R _A (dbA)	a _w
≥ 37,0	≥ 36,2	0,80

^{*} Consult certificates.

Fire Reaction classification

A2-s1, d0 according EN-13501-1.

Fire Resistance

N.A. (Not applicable).

Range of application and behavior in the presence of water

- Temperature between -40 °C and +180°C
- Not hydrophilic.
- *These are specific maximum temperatures, with the panel properties only guaranteed up to 100°C if it is a continuous temperature.

Span Table

Single span condition.

Load kg/m²	30	60	80	100	120	150	200	
Span (m)	* Under consultation with technical assistance ACH Panels							

Quality

Quality control complying with UNE EN 10204.

Saint-Gobain

Making the world a better home.

Customer service info@panelesach.com

Contact us

C/ Los Corrales. Parcelas C5 y C6
Polígono Industrial "La Ballestera"

