

ACH PARTITIONING PANEL

200 mm mm thick, Mineral Wool core - Density type "L"


Profile and side joint PF1



Standard profile



Micro ribbed profile



Flat profile

Description

ACH Partitioning panel (PF1) is manufactured with two pre painted steel sheets, bonded with organic glued to the mineral core.

The steel sheets fulfill the EN10346 standards and they are available from 0,5 mm to 1,00 mm thick, being 0,5 mm ACH,s standard thickness.

To meet each project special appliance, ACH offers several coating options: SP25, PVDF25, PVDF35, HDS35, HDX55, PRISMA55, HPS200, etc. All according to EN 10169. ACH standard coating is 25 µm Polyester (SP25).

ACH Partitioning panel (PF1) can be manufactured with other materials, upon request: aluminum, stainless steel, etc.

The mineral core is produce according to EN13162 standard.

Applications

ACH Partitioning panel (PF1) is a secret fixings insulated panel specially designed for industrial and large buildings construction, as well as ceilings.

ACH Partitioning panel (PF1) are recommended for the construction of interior division walls and facades of:

- Warehousing: small, medium or large size, usually heated
- Acoustic insulation inside industrial buildings.
- When fire protection is required or established by the Building Regulations and Standards.
- Parking and garage Firewalls, to prevent fire propagation.
- Data Centers, where fire suppression is obligatory, in addition to high temperatures and noise insulation.
- Storage buildings designed for flammable and/or combustible substances storage

Advantages

ACH prefabricated panels advantages are: easy and fast installation, lighter structure, higher finishing quality, fire protection, acoustic and thermal insulation, time and cost saving, with the best quality certification.

Performance

Thick. mm	Width mm	Max. recommended length: m	Core's type	Weight kg/m ²	Thermal transm. W/m ² K
200	1.150	12,00	L	26,2	0,194

Acoustics*

R _w (dB)	R _A (dB)
≥31	≥30,5

* Consult certificates.

Fire Raction classification

A2-s1, d0 according EN-13501-1.

Fire Resistance

NA (Not applicable)

Range of application and behavior in the presence of water

- Temperature between -40°C and +180°C.
- Not hydrophilic.

*These are specific maximum temperatures, with the panel properties only guaranteed up to 100°C if it is a continuous temperature

Span table

Single span condition

Load kg/m ²	30	60	80	100	120	150	200
Span (m)	*Under consultation with technical assistance ACH PANELS						

Deflection limit L/180. Security coefficient: 1,8

Quality

CE Quality control complying with UNE EN 14509.